



## Low Odor Formula

Bitumar utilizes a liquid low odor suppressant (not a masking agent) that greatly reduces if not eliminates the asphalt odor.

Bitumar's Low Odor BUR Asphalt is available in BUR-PAK, Cartons and Bulk.

All Bitumar BUR Asphalt is low odor at no additional charge.

### B.U.R Type III

Characteristics	Method	Specifications		Typical Characteristic
		ASTM D 312	CSA 123.4-04	
Flash Point (C.O.C.)	ASTM D92	260 (500) min.	260 (500) min.	>260 (500)
Softening Point	ASTM D36	85-96 (185-205)	90-98 (194-208)	95 (203)
Penetration @ 25°C (77°F) 100g, 5s	ASTM D5	15-25	15-25	18
Ductility @ 25°C (77°F) 5cm/min	ASTM D6	2.5 min	N/A	3.5
Volatilization 5h, 163°C (325°F) loss in weight	ASTM D6	1.0 max	1.0 max	0.05
Solubility in Trichloroethylene	ASTM D2042	99.0 min	99 min	99.8
EVT (mop application)		445±25		